

**Listing of Claims**

1. (Original) A breathable laminate having an MVTR of at least about 300 g/m/24 hours comprising a nonwoven support layer bonded to an oriented film comprising a letdown resin phase wherein said letdown resin comprises an ethylene copolymer having a density less than about 0.915 and a melt index of 6 or less and a filled carrier resin phase comprising a different ethylene polymer or copolymer having a density at least about 0.003 g/cc greater than that of said letdown resin.
2. (Original) The breathable laminate of claim 1 wherein the density of the film letdown resin is less than about 0.913 g/cc.
3. (Original) The breathable laminate of claim 2 wherein the density of the film letdown resin is in the range of from about 0.900 g/cc to about 0.912 g/cc.
4. (Original) The breathable laminate of claim 3 wherein the carrier resin ethylene polymer or copolymer has a density at least about 0.007 g/cc higher than that of said letdown resin.
5. (Original) The breathable laminate of claim 1 wherein the carrier resin ethylene polymer or copolymer has a melt index of at least about 10 g/10 min.
6. (Original) The breathable laminate of claim 5 wherein the carrier resin ethylene polymer or copolymer has a melt index of at least about 20 g/10 min.
7. (Original) The breathable laminate of claim 1 having a film basis weight in the range of from about 13 gsm to about 25 gsm.
8. (Original) The breathable laminate of claim 4 having a film basis weight in the range of from about 13 gsm to about 25 gsm.
9. (Original) The breathable laminate of claim 1 wherein the film has a calcium carbonate filler concentration based on the total film composition in the range of from about 30% to about 70% by weight.
10. (Original) The breathable laminate of claim 8 wherein the film has a calcium carbonate filler concentration based on the total film composition in the range of from about 30% to about 70% by weight.
11. (Original) The breathable laminate of claim 1 wherein both film ethylene copolymers are selected from the group consisting of LLDPE.
12. (Original) The breathable laminate of claim 10 wherein both film ethylene copolymers are selected from the group consisting of LLDPE.
13. (Original) The breathable laminate of claim 1 wherein said nonwoven comprises a spunbond nonwoven.

14. (Original) The breathable laminate of claim 12 wherein said nonwoven comprises a spunbond nonwoven.
15. (Original) The breathable laminate of claim 1 wherein said nonwoven comprises a bonded carded web.
16. (Original) The breathable laminate of claim 12 wherein said nonwoven comprises a bonded carded web.
17. (Original) The breathable laminate of claim 1 wherein said nonwoven comprises more than one layer.
18. (Original) The breathable laminate of claim 14 wherein said nonwoven comprises more than one layer.
19. (Original) The breathable laminate of claim 1 wherein said film comprises more than one layer.
20. (Original) The breathable laminate of claim 14 wherein said film comprises more than one layer.
21. (Original) The breathable laminate of claim 1 wherein said film has a break strain in the cross machine direction of greater than 300%.
22. (Original) The breathable laminate of claim 14 wherein said film has a break strain in the cross machine direction of greater than 300%.
23. (Original) The breathable laminate of claim 1 having a MVTR of about 5000 g/m/24 hours to about 10,000 g/m/24 hours.
24. (Original) The breathable laminate of claim 1 wherein said film higher density ethylene copolymer has a density greater than 0.915 g/cc.
25. (Original) The breathable laminate of claim 14 wherein said letdown resin phase and said carrier resin phase comprise a layer constituting at least about 90% of the total film thickness.
26. (Original) A personal care product comprising the breathable film laminate of claim 1.
27. (Original) A disposable diaper comprising the breathable film laminate of claim 1 as a backing component.